

PRODUCT DATA SHEET

Sika® Injection-101 RC

FAST FOAMING PUR-INJECTION RESIN FOR TEMPORARY WATER-STOPPING

DESCRIPTION

Sika® Injection-101 RC is a low viscosity, fast foaming and solvent free water reactive polyurethane injection resin, which cures to a dense flexible foam with a fine cellular structure.
Suitable for use in hot and tropical climatic conditions.

USES

Sika® Injection-101 RC may only be used by experienced professionals.

- Sika® Injection-101 RC is used for the temporary waterstopping of high water intrusions in cracks, joints and cavities in concrete, brickwork and natural stonework.
- To achieve permanent watertight crack sealing, Sika® Injection-201 CE should be injected subsequently.

CHARACTERISTICS / ADVANTAGES

- No reaction takes place unless it is in direct contact with water.
- Sika® Injection-101 RC can be injected as a single component system.
- The free foaming expansion in contact with water is up to 40 times.
- The reaction speed (foam formation) is influenced by the temperatures of the mixed material, the structure and the contact water, plus the hydrodynamic conditions.

APPROVALS / STANDARDS

German KTW drinking water certificate
German ZTV-ING chapter 3, part 5 (RISS) tested (BAST listed)

PRODUCT INFORMATION

Chemical base	Water reactive 2-part polyurethane resin, solvent and CFC free		
Packaging	Part A	10 or 20 kg	
	Part B	12.5 or 25 kg	
Colour	Part A	Colourless	
	Part B	Brown	
Shelf life	24 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.		
Storage conditions	Dry storage at temperatures from +5 °C up to +35 °C. Protect from direct sunlight and humidity.		
Density	Part A	~1.0 kg/l	(ISO 2811)
	Part B	~1.25 kg/l	
	(20 °C)		

Viscosity	Part A	~140 mPa·s	(ISO 3219)
	Part B	~155 mPa·s	
(20 °C)			

TECHNICAL INFORMATION

Expansion	Expansion start	~15 s after contact with water	(EN 1406)
	Expansion end	~67 s	
(20 °C)			

APPLICATION INFORMATION

Mixing ratio	Part A : Part B = 1 : 1 (by volume)		
	Reaction time of Sika® Injection-101 RC (PM 10081-11)		
	Material temperature	Expansion start	Expansion end
	+5 °C	~19 s	~79 s
	+10 °C	~17 s	~88 s
	+20 °C	~16 s	~70 s
The given data are laboratory parameters and may deviate depending on the object and conditions on site.			
Ambient Air Temperature	+5 °C min. / +35 °C max.		
Substrate Temperature	+5 °C min. / +35 °C max.		
Pot Life	~2 h (20 °C) Remove skin from the surface (do not mix in!)		(ISO 9514)

APPLICATION INSTRUCTIONS

MIXING

Empty parts A and B into a mixing vessel and mix slowly and thoroughly for at least 3 minute (maximum 250 rpm) until homogeneous, thereby observing the safety precautions. The containers are supplied according to the required mixing ratio of 1 : 1 parts by volume.

Partial quantities can be measured out in separate vessels. After mixing, pour the material into the pump's feed container, stir briefly and apply within the pot life.

After mixing, pour the material into the pump's feed container, stir briefly and use within the pot life.

APPLICATION METHOD / TOOLS

Use injection pumps suitable for single part injection products.

CLEANING OF TOOLS

Clean all tools and application equipment as soon as possible and in accordance the Product Data Sheet for the Sika® Injection Cleaning System. Alternatively Sika® Colma Cleaner can be used to remove any polyurethane residue immediately after use. Do not leave Sika® Colma Cleaner in the injection pump Hardened / cured material can only be removed mechanically.

LIMITATIONS

Sika® Injection-101 RC is generally used for the temporary stopping of high water infiltration. To achieve permanent watertight crack sealing, the subsequent injection of Sika® Injection-201 CE is recommended.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF
Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF
UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA
Riyadh / Jeddah / Dammam
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

SikaInjection-101RC_en_AE_(02-2017)_1_1.pdf

Product Data Sheet
Sika® Injection-101 RC
February 2017, Version 01.01
020707010010000001