

PRODUCT DATA SHEET

Sikadur® PF

EPOXY RESIN PORE SEALING AND SMOOTHING PUTTY

DESCRIPTION

Sikadur® PF is a moisture tolerant, thixotropic, 2-component repair putty, based on a combination of epoxy resins and special selected high strength fillers. Suitable for use in hot and tropical conditions.

USES

Sikadur® PF may only be used by experienced professionals.

As a adhesive and mortar for:

- Concrete elements
- Hard natural stone
- Ceramics tiles, fibre cement
- Mortar, bricks, masonry
- Steel, iron, aluminium
- Wood
- Polyester, epoxy
- Glass
- Crack and surface sealing

As a fast setting rapid repair adhesive and mortar:

- Corners and edges
- Holes and void filling
- For vertical and overhead use

As a joint filling and crack sealing:

- Joint arris repair and crack sealing

CHARACTERISTICS / ADVANTAGES

Sikadur® PF has the following advantages:

- Easy to mix and apply
- High strength surface repair material
- Very good adhesion to most construction materials
- High strength adhesive
- Thixotropic: non-sag in vertical and overhead applications
- Non-shrink
- Different coloured components (for mixing control)
- No primer needed
- High initial and ultimate mechanical strength
- Good abrasion resistance
- Impermeable to liquids and water vapour
- Good chemical resistance

PRODUCT INFORMATION

Composition	Epoxy resin
Packaging	Part A: 4 kg container Part B: 2 kg container (A + B) 6 kg ready to mix units
Colour	Grey (Mixed A + B) Component A: White Component B: Black
Shelf life	24 months from date of production.

Storage conditions Store in original, unopened, sealed and undamaged packaging in dry condition at temperatures between +5 °C and 30 °C. Protect from direct sun light and moisture.

Density ~1.75 kg/l (mixed resin)

TECHNICAL INFORMATION

Shore D Hardness 70 - 80 (ASTM D-2240)
For full hardness: 7 d (25 °C)

Compressive Strength

25° C	1 Day	7 Days	14 Days	(ASTM C 579)
	≥ 35 N/mm ²	≥ 46 N/mm ²	≥ 50 N/mm ²	

Tensile Adhesion Strength > 1.5 N/mm² (ASTM C 882-99)

APPLICATION INFORMATION

Mixing Ratio Component A : Comp. B = 2 : 1 (by weight and volume)

Consumption ~1.75 kg / m² / mm
This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level or wastage etc.

Layer Thickness Maximum 3 mm in one single layer.

Ambient Air Temperature +5° C min. / +45° C max.

Dew Point Beware of condensation.
Substrate temperature during application must be at least 3 °C above dew point.

Substrate Temperature +5° C min. / +45° C max.

Pot Life ~45 min. (25 °C)
*200 g
The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill components A and B before mixing them (not below +5 °C).

Curing Time Sikadur® PF can be over coated with various Sikafloor®, Sikadur® and Sikagard® resins after 12 hours and not later than 24 hours at 30 °C.
Sikadur® PF is fully cured after 7 days. For more details please contact Sika Technical Department.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

- The substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².
- The substrate must be clean and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc..
- Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.
- Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.
- All dust, loose and friable material must be completely removed from all surfaces before application

of the product, preferably by brush or vacuum.

MIXING

Mix components (A and B) together for at least 3 minutes with a mixing paddle attached to a slow speed electric drill (maximum 400 rpm) until the material becomes smooth in consistency and an even grey colour of the mixture is obtained. Avoid aeration while mixing. Sikadur® PF is supplied ready for use and only has to be thoroughly stirred.

APPLICATION METHOD / TOOLS

When using a thin layer adhesive, apply the mixed adhesive to the prepared surface with a spatula, trowel, notched trowel.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be removed by mechanical means.

IMPORTANT CONSIDERATIONS

When applying to damp concrete (no standing/run-ning water), work well into substrates.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

Product Data Sheet

Sikadur® PF

October 2017, Version 01.01
020204030010000074

SikadurPF-en-AE-(10-2017)-1-1.pdf

