

PRODUCT DATA SHEET

SikaLatex[®] LB

WATER RESISTANT BONDING AGENT AND MORTAR ADMIXTURE

DESCRIPTION

SikaLatex[®] LB is a synthetic rubber emulsion Non-Toxic and non-corrosive that is used as admixture for cementitious bonding bridges and high-quality site-mix mortars.

USES

SikaLatex[®] LB is used as bonding agent and site-mix mortar admixture for the following applications:

- Grouts and screeds
- Patch repair mortars
- Masonry mortars
- Renders
- Bonding slurry between old and new concrete
- Tile adhesives

CHARACTERISTICS / ADVANTAGES

The main advantages of SikaLatex[®] LB are:

- Increased adhesion
- Reduced shrinkage and cracking
- Freeze thaw resistance
- Increased abrasion resistance
- Reduced permeability
- Improved workability
- Greater elasticity.
- Excellent water resistance.
- User friendly
- Suitable on most common construction substrates

PRODUCT INFORMATION

Composition	Styrene butadiene emulsion
Packaging	5, 20,1000 Kg
Appearance / Color	White liquid
Shelf life	12 months from date of production.
Storage conditions	Store properly in undamaged original sealed packaging, in dry cool conditions at temperatures between 5 °C and 30 °C. Protect from direct sunlight, frost, and contamination.
Density	~1.01 + 0.02 kg/l
Total Chloride Ion Content	≤0.1%

APPLICATION INFORMATION

Recommended Dosage

Bonding bridge by volume

SikaLatex® : Water = 1 : 1

Mortar

SikaLatex® : Water = 1 : 1 to 1 : 3

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The substrate shall be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by cementitious materials. De-laminated, weak, damaged, and deteriorated substrate shall be removed by suitable means before application. Rust, scale, dust, and other loose and deleterious materials which reduces bond or contributes to corrosion shall be removed.

MIXING

Mix SikaLatex® LB with the correct amount of water to produce a gauging solution. Do not add neat SikaLatex® LB to a mortar mix. Pour part of the gauging solution into a suitable mixing container. While stirring slowly, add the cement- sand mix to the gauging solution and mix thoroughly until a smooth, uniform and lump-free mix is achieved. Do not over mix mortars containing SikaLatex® LB. Within the mixing time add additional gauging solution to adjust to the desired consistency.

APPLICATION METHOD / TOOLS

Bonding Bridge

Thoroughly pre-wet the prepared substrate a recommended 2 hours before application. Keep the surface wet and do not allow to dry. Before application remove excess water e.g. with a clean sponge. The surface shall appear a dark matt appearance without glistening and surface pores and pits shall not contain water. Using a stiff clean brush work the mix vigorously onto the substrate, forming a thin layer filling all unevenness, pits, and pores.

Mortar

Always apply following layer of mortar "wet on wet" onto bonding bridge.

IMPORTANT CONSIDERATIONS

Never use pure SikaLatex® LB or SikaLatex® LB-water mix directly onto the substrate as bonding bridge, always add cement and sand to the mix.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Sika Near East

Secteur 5, Rue 70
Jisr el Bacha Beirut
Tel: +961 1 510270
lbn.sika.com

PRODUCT DATA SHEET
SikaLatex® LB
October 2020, Version 01.0
020301010010000310

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological, and other safety related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaLatex LB-en-(03-2017)-1.pdf