

PRODUCT DATA SHEET

Sika® Injection-201 CE

ELASTIC PUR-INJECTION RESIN FOR PERMANENT WATERTIGHT SEALING



DESCRIPTION

Sika® Injection-201 CE is a very low viscosity, elastic and solvent free polyurethane injection resin. In contact with water, a uniform, closed and therefore watertight pore structure forms, which is elastic and flexible.

Suitable for use in hot and tropical climatic conditions.

USES

Sika® Injection-201 CE may only be used by experienced professionals.

- Sika® Injection-201 CE is used for permanent watertight sealing with some flexibility to absorb limited movement, in dry, damp or water-bearing cracks and joints in concrete, brickwork and natural stone
- Sika® Injection-201 CE can be used for the injection of the SikaFuko®-System (non re-injectable!)
- For use in water-bearing cracks under hydrostatic pressure, preliminary injection shall be made with Sika® Injection-101 RC

CHARACTERISTICS / ADVANTAGES

- Permanently elastic, can absorb limited movements
- No shrinkage in subsequent dry conditions
- Due to its low viscosity it can penetrate into cracks >0.2 mm in width
- Cured Sika® Injection-201 CE is inert and chemically-resistant
- Solvent-free
- Can be injected as a one component system

APPROVALS / STANDARDS

- German KTW drinking water certificate
- Concrete injection for ductile filling of cracks, voids and interstices (D) according to EN 1504-5:2004, Declaration of Performance 35859175, certified by notified factory production control certification body 0761 and provided with the CE marking.
- Sika® Injection-201 CE complies with the requirement of specification BS 6920: Part 2 & 3 2000 Cl. 2.2 & 2.3 (Suitability of non-metallic products for use in contact with water intended for human consumption with regard to their effect on the quality of the water)

PRODUCT INFORMATION

Chemical base	Water reactive 2-part polyurethane resin, solvent free	
Packaging	Part A	10 kg, 20 kg
	Part B	10.6 kg, 21.2 kg
Colour	Part A	Colourless
	Part B	Brown
Shelf life	36 months from date of production if stored properly in undamaged, unopened, original sealed packaging.	
Storage conditions	Dry storage at temperatures between +5 °C and +35 °C. Protect from direct sunlight and humidity.	

Density	Part A	Part B	(ISO 2811)
	~1.00 kg/l	~1.07 kg/l	
All density values determined at +20 °C			
Viscosity	~100 mPa·s (Mixture, +20 °C)		

TECHNICAL INFORMATION

Shore A Hardness	~43 (7 d)	
Modulus of Elasticity in Flexure	~2 MPa	(ISO 527-1)
Elongation at Break	~35 %	(ISO 527)

APPLICATION INFORMATION

Mixing ratio	Part A : Part B - 1 : 1 parts by volume			(ISO 9514)
	Reaction time of Sika® Injection-201 CE			
Material Temperature	+5 °C			
	~180 min			
	+10 °C			
	~180 min			
+20 °C			~135 min	
The given data are laboratory parameters and may deviate depending on the object and conditions on site.				
Ambient Air Temperature	+5 °C min. / +35 °C max.			
Substrate Temperature	+5 °C min. / +35 °C max.			

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Surfaces of cavities and cracks need to be clean, free of loose particles, dust, oil and any other bond-breaking substances. Any dirt must be blown out by compressed air.

MIXING

Empty parts A and B into a mixing vessel and mix slowly and thoroughly for at least 3 minute (maximum 250 rpm) until homogeneous, observing the safety precautions. The containers are supplied according to the required mixing ratio of 1 : 1 parts by volume. Partial quantities can be measured out into separate vessels. After mixing, pour the material into the pump's feed container, stir briefly and use within the pot life.

CLEANING OF TOOLS

Clean all tools and application equipment as soon as possible and in accordance the Product Data Sheet for the Sika® Injection Cleaning System. Alternatively Sika® Colma Cleaner can be used to remove any polyurethane residue immediately after use. Do not leave Sika® Colma Cleaner in the injection pump. Hardened / cured material can only be removed mechanically.

LIMITATIONS

Only for application by trained and experienced professionals. For water intrusions that can not be stopped with Sika® Injection-201 CE, the fast foaming PUR injection resin Sika® Injection-101 RC can be injected until the water flow stops.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF
Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF
UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA
Riyadh / Jeddah / Dammam
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

SikaInjection-201CE_en_AE_(02-2017)_1_1.pdf

Product Data Sheet
Sika® Injection-201 CE
February 2017, Version 01.01
020707010020000001